

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 290/04, C08L 51/00, C09J 151/00		A1	(11) International Publication Number: WO 98/37111
			(43) International Publication Date: 27 August 1998 (27.08.98)
(21) International Application Number: PCT/US98/02696 (22) International Filing Date: 23 February 1998 (23.02.98) (30) Priority Data: 08/803,594 21 February 1997 (21.02.97) US 08/805,042 21 February 1997 (21.02.97) US (71) Applicant: ADHESIVES RESEARCH, INC. [US/US]; P.O. Box 100, Glen Rock, PA 17327 (US). (72) Inventors: ZAJACZKOWSKI, Michael, J.; 2595 West Philadelphia Street, York, PA 17404 (US). STUTZMAN, Barbara, A.; 860 Butter Road, Dover, PA 17315 (US). THERRIAULT, Donald, J.; 4180 Stone Run Drive, York, PA 17402 (US). (74) Agents: HELLWEGE, James, W. et al.; P.O. Box 2266 Eads Station, Arlington, VA 22202 (US).			(81) Designated States: CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: TRANSDERMAL PRESSURE SENSITIVE ADHESIVE DRUG DELIVERY SYSTEM AND PRESSURE SENSITIVE ADHESIVE USED THEREIN			
(57) Abstract A graft copolymer pressure sensitive adhesive is provided comprised of a backbone polymer having a polymeric moiety grafted thereto. The copolymer comprises at least one A monomer consisting of a monomeric (meth)acrylic acid ester of a non-tertiary alcohol, optionally at least one B monomer, optionally at least one polymeric graft moiety C having a T_g greater than 20 °C, and a macromeric graft moiety D containing repeat hydrophilic units. The adhesive may be used with advantage in a transdermal drug delivery system in homogeneous admixture with a pharmacologically active agent.			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TRANSDERMAL PRESSURE SENSITIVE ADHESIVE
DRUG DELIVERY SYSTEM AND PRESSURE
SENSITIVE ADHESIVE USED THEREIN

BACKGROUND OF THE PRESENT INVENTION

5 The present invention is directed to a pressure sensitive adhesive useful in transdermal administration of pharmacologically active agents, in particular estrogen and/or progestin active agents.

10 The transdermal delivery of therapeutic agents has been the subject of intense research and development for over 20 years. These efforts have resulted in the creation of several commercially successful products whose advantages
15 over other dosage forms are well documented. The skin, however, is an exceptionally well designed barrier. As a result, only a relatively small number of drug molecules are suitable for transdermal delivery, including hormones such as
20 estrogen and/or progestin.

 It is known to administer steroidal hormones such as estrogen and/or progestin active agents by transdermal means to a patient. See, for example, U.S. Patent Nos. 5,108,995; 5,223,261; 5,242,951;
25 5,422,119; 5,460,820; and WO 96/08229. It has been found that such active agents are susceptible to crystallization within the adhesive matrix over time. Such crystallization inhibits the ability of the transdermal device to deliver the active
30 agent to the patient.

 The prior art does not provide a transdermal pressure sensitive adhesive which both serves as a satisfactory matrix for the delivery of an estrogen and/or progestin active agent as well as

inhibiting the crystallization of such active agent in order to enhance the long-term effectiveness of the delivery system.

It is also desirable to provide a transdermal adhesive which may be used with either an oily or water-soluble drug flux or skin permeation enhancer or mixtures of same. This avoids the need to use separate adhesive formulations depending upon whether the enhancer is oil or water-soluble.

OBJECTS AND SUMMARY OF THE INVENTION

It is therefore an object of the present invention to provide a pressure sensitive adhesive drug delivery system which possesses acceptable compatibility with active drug agents while maintaining the appropriate viscoelastic characteristics for adequate skin adhesion.

It is also an object of the present invention to provide a pressure sensitive adhesive drug delivery system which reduces the tendency of hormones to crystallize within the transdermal drug delivery system.

It is further an object of the present invention to provide a pressure sensitive adhesive which exhibits hydrophilic properties.

It is yet another object of the present invention to provide a pressure sensitive adhesive which possesses adequate compatibility with both oily and water-soluble percutaneous penetration enhancers and which may accordingly be used with advantage in a transdermal drug delivery device.

In accordance with the present invention, there is thus provided a graft copolymer pressure sensitive adhesive comprised of a backbone polymer

having a polymeric moiety grafted thereto, said graft copolymer comprising the reaction product of:

- (1) at least one A monomer consisting of a monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol, said alcohol having from 1 to 30 carbon atoms, wherein at least about 30 percent by weight of said A monomer consists of a monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol having at least 12 carbon atoms, and said at least one A monomer exhibiting an average number of carbon atoms in the alcohol portion of the total acrylic or methacrylic acid esters of at least 10;
- (2) optionally at least one B monomer;
- (3) optionally at least one polymeric graft moiety C having a T_g greater than 20°C , and
- (4) a polymeric graft moiety D containing repeat hydrophilic units, preferably a polyether or polyester-based graft moiety.

In accordance with the present invention, there is also provided a transdermal drug delivery composition having pressure sensitive adhesive properties comprised of (1) a graft copolymer comprised of a (meth)acrylic ester backbone copolymer optionally including at least one N-vinyl lactam monomer and having a polymeric moiety grafted thereto containing hydrophilic repeat units, and (2) a pharmacologically active agent in homogeneous admixture with said macromer reinforced base polymer.

In accordance with the present invention, there is still further provided a transdermal drug delivery system for administering a pharmacologically active agent comprising a

flexible backing material impermeable to said pharmacologically active agent and an adhesive layer on at least a portion of said backing material, the improvement wherein said adhesive layer comprises a graft copolymer comprised of a (meth)acrylic ester backbone copolymer optionally including at least one N-vinyl lactam monomer and having a polymeric moiety grafted thereto containing hydrophilic repeat units.

10 DETAILED DESCRIPTION OF THE INVENTION

The present invention is directed to a pressure sensitive adhesive as well as a transdermal drug delivery composition comprised of a graft copolymer and transdermal delivery device utilizing such a composition.

The graft copolymer pressure sensitive adhesive employed in the present invention is comprised of a backbone polymer having a polymeric moiety grafted thereto. The graft copolymer comprises the reaction product of at least one (meth)acrylic acid ester A monomer (as defined), at least optional B monomer, optionally a polymeric graft moiety C having a T_g greater than 20°C, and a polymeric graft moiety D containing hydrophilic repeat units.

The graft copolymer includes at least one A monomer consisting of a monomeric (meth)acrylic acid ester of a non-tertiary alcohol where the alcohol portion has from 1 to 30 carbon atoms. Exemplary A monomers include but are not limited to esters of acrylic acid or methacrylic acid with non-tertiary alcohols such as 1-butanol, 1-pentanol, 2-pentanol, 3-pentanol, 2-methyl-1-butanol, 1-methyl-1-pentanol, 2-methyl-1-pentanol,

3-methyl-1-pentanol, 2-ethyl-1-butanol, 3,5,5-trimethyl-1-hexanol, 3-heptanol, 2-octanol, 1-decanol, 1-dodecanol, etc.

Advantageously, it has been found useful to
5 employ at least one A monomer formed from an alcohol having at least 12 carbon atoms. The use of an A monomer formed from an alcohol having at least 18 carbon atoms is particularly desirable. Such exemplary A monomers include but are not
10 limited to lauryl acrylate (C_{12}), tridecylacrylate (C_{13}), myristyl acrylate (C_{14}), palmityl acrylate (C_{16}), and stearyl acrylate (C_{18}). Such monomers are known to those skilled in the art.

The presence of an A monomer having a carbon
15 chain of at least 12 carbon atoms has been found to enhance the compatibility of the adhesive with oily or non-water-soluble drug flux or skin permeation enhancers which may be employed. Such enhancers have not been found to be particularly
20 compatible with conventional transdermal adhesives containing a major portion of A monomers formed from alcohols having from 4 to 12 carbon atoms. While the use of A monomers formed from alcohols having from 4 to 12 carbon atoms in the adhesive
25 of the present invention is appropriate, it is preferable for the at least one A monomer component to comprise at least 30 percent by weight of an A monomer formed from an alcohol having greater than 12 carbon atoms. The at least
30 one A monomer component (if more than one A monomer is present) will exhibit an average number of carbon atoms in the alcohol portion of the total acrylic or (meth)acrylic acid esters of from 4 to 16, and preferably at least 10.

One or more optional polymerizable B monomers may be incorporated in the copolymer which B monomer(s) is copolymerizable with the A monomer. Such additional B monomer(s) may be either hydrophilic or hydrophobic.

Exemplary optional B monomers include vinyl monomers having at least one nitrogen atom. Such monomers (each of which exhibit a T_g of $>20^\circ\text{C}.$) include but are not limited to N-mono-substituted acrylamides such as acrylamide, methacrylamide, N-methylacrylamide, N-ethylacrylamide, N-methylolacrylamide, N-hydroxyethylacrylamide, and diacetone acrylamide; N,N-disubstituted acrylamides such as N,N-dimethylacrylamide, N,N-diethylacrylamide, N-ethyl-N-aminoethylacrylamide, N-ethyl-N-hydroxyethylacrylamide, N,N-dimethylolacrylamide, and N,N-dihydroxyethylacrylamide, etc.

Other optional B monomers may include, for example, various vinyl monomers such as acrylic and methacrylic acid, methoxyethyl acrylate, or methacrylate, ethoxyethyl acrylate or methacrylate, glycerol acrylate or methacrylate, hydroxyethyl methacrylate, hydroxypropyl methacrylate, beta-carboxyethyl acrylate, vinyl pyrrolidone and vinyl caprolactam (each of which also exhibit a T_g of $>20^\circ\text{C}.$).

The at least one B monomer preferably comprises an N-vinyl lactam monomer. Exemplary N-vinyl lactam monomers include but are not limited to N-vinyl-2-pyrrolidone; 5-methyl-N-vinyl-2-pyrrolidone; 5-ethyl-N-vinyl-2-pyrrolidone; 3,3-dimethyl-N-vinyl-2-pyrrolidone; 3-methyl-N-vinyl-2-pyrrolidone; 3-ethyl-N-vinyl-2-pyrrolidone; 4-methyl-N-vinyl-2-pyrrolidone; 4-ethyl-N-vinyl-2-

pyrrolidone; N-vinyl-2-valerolactam; N-vinyl-2-caprolactam; and mixtures of any of the foregoing. Preferably, the N-vinyl lactam is N-vinyl-2-pyrrolidone.

5 The optional graft polymeric moiety C has a T_g greater than 20°C . Graft polymeric moiety C has the formula X-Z wherein X is a group copolymerizable with monomers A and B or capable of attachment to copolymerized A and B monomers
10 and Z is a polymeric graft moiety having a T_g greater than 20°C . The Z moiety is essentially unreactive under copolymerization conditions.

 More specifically, the X moiety is an unsaturated polymerizable moiety the composition
15 of which is not critical. The X moiety may be, for example, when intended to be copolymerizable with monomers A and B, simply a vinyl group of the formula $\text{CHR}=\text{CR}^1$ - where R is hydrogen or COOH and R^1 is hydrogen or alkyl such as methyl. Other
20 exemplary X moieties include but are not limited to methacryloyl, maleoyl, itaconoyl, crotonoyl, unsaturated urethane moiety, methacrylamido and moieties of the formula $\text{CH}_2=\text{CHCH}_2\text{O}-$.

 The X moiety may comprise an amine or alcohol
25 moiety (such as a monohydroxyl or monoamine moiety) which permits attachment of the macromer to a suitable functionality on previously-polymerized monomers A and B. For instance, the hydroxyl moiety can serve as a terminal reactive
30 group by reaction with suitable moieties on the polymer backbone resulting from the use of monomers such as isocyanate-substituted (meth)acrylic acid, (meth)acrylic acid anhydride, etc.

A variety of functional groups may be employed to attach the graft Z to the polymer backbone.

Exemplary functional groups include but are

5 not limited to $\begin{array}{c} \text{O} \\ \parallel \\ -\text{C}-\text{O}-\text{CHR}-\text{CH}_2- \end{array}$; $\begin{array}{c} \text{O} \\ \parallel \\ -\text{C}-\text{O}-\text{CH}_2\text{CH}_2-\text{NH}-\text{C}-\text{O}- \\ \parallel \\ \text{O} \end{array}$
 $\text{CHR}-\text{CH}_2-$; $\begin{array}{c} \text{O} \\ \parallel \\ \text{CH}_2-\text{O}-\text{CHR}-\text{CH}_2- \end{array}$; $\begin{array}{c} \text{O} \\ \parallel \\ -\text{O}-\text{C}-\text{CH}_2-\text{O}-\text{CHR}-\text{CH}_2- \end{array}$; and
 $-\text{OCH}_2\text{CH}_2-\text{O}-\text{CHR}-\text{CH}_2-$

10 where R is a hydrogen atom or a lower alkyl group.

With regard to the optional polymeric graft moiety C portion of the adhesive composition, U.S. Patent Nos. 3,786,116; 3,842,057; 3,842,058; 3,842,059; 3,862,098; 3,862,101, 3,862,102 and
 15 4,554,324 disclose polymerizable macromers which are suitable for use as graft moieties on a backbone polymer as defined.

Preferably, the polymeric moiety C is formed from a vinyl aromatic monomer such as styrene,
 20 alpha-methylstyrene, indene and p-tert-butylstyrene. However, the polymeric moiety Z may also be formed from vinyl toluene, acenaphthalene, acrylonitrile and methacrylonitrile; organic isocyanates including lower alkyl, phenyl, lower
 25 alkyl phenyl and halophenyl isocyanates; organic diisocyanates including lower alkylene, phenylene, and tolylene diisocyanates; lower alkyl and allyl acrylates and methacrylates; including methyl, t-butyl acrylates, and methacrylates; lower olefins,
 30 such as ethylene, propylene, butylene, isobutylene, pentene, hexene, etc.; vinyl esters of aliphatic carboxylic acids such as vinyl acetate, vinyl propionate, vinyl octoate, vinyl oleate, vinyl stearate, vinyl benzoate, vinyl
 35 lower alkyl ethers; conjugated dienes such as

5 The selection of the specific polymerizable monomer for the polymer graft is not critical, since as the above listing suggests, a wide variety of monomers (and the resulting polymeric moieties) can be used with success as a polymeric graft in the claimed composition which meet the minimum T_g requirement.


The molecular weight of the graft polymeric moiety C is preferably sufficient to result in the formation of a "phase-separated" graft copolymer composition. Generally the molecular weight of the graft polymeric moiety will be within the range of from 2,000 to 60,000, and will preferably range from 2,000 to 13,000.

The macromer D also forms polymeric sidechains on the graft copolymer. The macromer D contains hydrophilic repeat units.

The macromer may be represented by the formula $X-(Y)_p-Z-R$. X is as defined above and is a moiety copolymerizable with monomers A and B or, in the alternative, capable of attachment to polymerized monomers A and B, Y is a divalent linking group, Z is a homo- or copolymeric moiety essentially unreactive at copolymerization conditions which contains hydrophilic repeat units, R is a terminal group, and p is 0 or 1.

A preferred Y divalent linking group is -C- ,
or a linking group which incorporates such a
moiety.

Additional Y linking groups which may be employed in connection with the present invention include but are not limited to the following moieties:



10
$$-\text{OCH}_2\text{CH}_2-\text{O}-\text{CR}_2-\text{CH}_2-; \text{ and } \begin{array}{c} \text{O} \quad \quad \quad \text{O} \\ \parallel \quad \quad \quad \parallel \\ -\text{C}-\text{O}-\text{CH}_2\text{CH}_2-\text{NH}-\text{C}-\text{O}- \\ \parallel \quad \quad \quad \parallel \\ \text{CR}_2-\text{CH}_2-; \end{array}$$
 where R is hydrogen, alkyl or phenyl. Obviously, the presence of the Y linking group is optional in the event the moiety includes a

15 functionality which enables the Z moiety to react with the X moiety. As the incorporation of macromolecular moieties in copolymers is well understood by those skilled in the art, the choice of a suitable X and Y moiety for use in the

20 present invention may be readily made upon practice of the present invention. See, for example, the discussion in U.S. Patent Nos. 3,786,116; 3,832,423; 3,842,058; 3,842,059; 3,842,146; and 4,554,324, herein incorporated by

25 reference.

The Z moiety is preferably selected from the group consisting of (but not limited to) a polypropylene or polyethylene oxide radical, a polyethyloxazoline radical such as a radical of


30 poly(2-ethyl-2-oxazoline), polyacrylic acid radical, polyvinyl alcohol radical, polyvinylpyrrolidone radical, polyvinyl caprolactam radical, polymethylvinyl ether radical or mixtures thereof. Exemplary D macromers formed

35 from such radicals include but are not limited to

ethoxylated or propoxylated hydroxy(C₁₋₅)alkyl meth(acrylate), polymethylvinyl ether mono(meth)acrylate and beta-carboxyethyl acrylate. The molecular weight of the macromer used in the present invention is not critical but will generally range from about 300 to about 50,000, and preferably from about 300 to 3,000.


The Z moiety is preferably comprised solely of one or more hydrophilic monomer radicals. However, the Z moiety may also be a copolymer of hydrophilic and hydrophobic monomers. Desirably, any non-hydrophilic portion employed in such a Z copolymer is present in an amount of less than 50 percent by weight based on the weight of the macromer, and preferably less than 30 percent by weight.

The macromer D is preferably represented by the formula:




wherein X and Y are as defined above and R represents a terminal group; and in which m is an integer of from 2 to 6 and n is an integer of up to 300. More specifically, macromer D may be an

ethoxylated or propoxylated hydroxy(C₁₋₅)alkyl (meth)acrylate, represented by the formula:



wherein R₁ is hydrogen or C₁₋₅ alkyl and R is a terminal group. Preferably, m is 2 or 3 and n is 5 to 30, and R is OH, C₁₋₅ alkyl or nonyl-phenol.

Alternatively, macromer D may advantageously comprise a 2-carboxy(C₁₋₅)alkyl acrylate of the formula:



wherein R_1 is hydrogen or C_{1-5} alkyl and R is a terminal group. Preferably, m is 2 or 3 and n is 4 to 30, and R is H, OH, C_{1-5} alkyl or nonyl-phenol.

Of course, macromer D may incorporate mixtures of polyether and polyester repeat units with advantage which ratios are non-critical to practice of the present invention.

The macromer D may employ a variety of terminal groups R. While the terminal group may typically be OH or C_{1-5} alkyl, it may be desirable to select a terminal group based on the functional character of the terminal group. For instance, suitable terminal groups include but are not limited to (1) acid/ionic groups such as carboxyl, phosphate or sulfate groups, (2) hydrophobic groups such as lower alkyl, phenyl or substituted phenyl, and (3) hydrophilic groups such as hydroxyl or amine groups.

Depending upon the terminal group employed, ionic end groups may be used to provide pH-dependent solubility characteristics for the copolymer. Hydrophobic terminal groups may be used to reduce the water solubility of the copolymer.

Other physical properties or characteristics of the copolymer may be modified by selection of suitable terminal groups. The copolymer of the present invention may be covalently or ionically crosslinked in a conventional manner. Ionic terminal groups may be used to provide a desired degree of crosslinking; for example, by neutralizing acid moieties with metal hydroxides.

High temperature performance may be enhanced by incorporating an acid functionality in conjunction with a ditertiary amine. Aqueous solution viscosities may be influenced by the presence of ionic terminal groups.

Preferably, the A monomer is present in the graft copolymer an amount of from 20 to 80 percent by weight, the B monomer is present in an amount of from 3 to 30 percent by weight, the optional C macromer is present in an amount of from 2 to 15 percent by weight, and the D macromer is present in an amount of from 5 to 60 percent by weight, based on the total weight of the respective components A, B, C, and D in the copolymer.

It may be advantageous to incorporate a tackifier or plasticizer into the copolymer to enhance tack. Exemplary tackifiers include but are not limited to polyethylene glycol, polypropylene glycol, and suitable polyoxyethylene-based compounds. Suitable polyoxyethylene-based tackifiers are disclosed at column 6 of U.S. Patent No. 4,413,080, herein incorporated by reference in its entirety. Other suitable tackifiers include conventional hydrogenated rosin ester compounds. Polyalicyclic tackifiers include those based on aromatic copolymers of styrene, alpha-methyl styrene and indene followed by hydrogenation. Such tackifiers, if present, may be employed in an amount of up to about 50 percent by weight, based on the total weight of the composition. Plasticizers may be used in amounts of up to about 20% by wt. Exemplary plasticizers include but are not limited to adipate and glutarate esters, hydrogenated rosin esters and reduced alcohol

derivatives, as well as hydrogenated poly(aromatic) copolymers and mineral or paraffin oils. Preferred plasticizers include citric acid esters such as those marketed under the name Citroflex which include triethyl citrate, acetyltriethyl citrate, tri-n-butyl citrate, acetyltri-n-butyl citrate.

As noted above, the copolymer composition of the present invention may be prepared by any conventional polymerization technique, including (1) free radical-initiated copolymerization of components A and D and optionally B and C in the presence of a solvent, or (2) attachment of the macromer grafts to a preformed backbone polymer formed from copolymerized monomer A copolymerized with monomer B via reaction with a suitable functional group on the backbone polymer subsequent to formation of same.

Suitable copolymerization temperatures range from about 20°C. to about 150°C. for periods of time of from 2 to 24 hours until the desired degree of conversion occurs. Upon completion of the copolymerization process, the solvent is removed and a tacky copolymer results having acceptable adhesive properties. If desired, a suitable crosslinking agent may be employed to increase the molecular weight of the adhesive if desired.

The composition of the present invention successfully overcomes the deficiencies of prior art transdermal adhesives in several ways. The inclusion of an N-vinyl lactam monomer as a B monomer reduces the tendency of any pharmacologically active agent susceptible to crystallization (such as estrogen and/or

progesterin) present in the drug delivery system to crystallize within the system. This permits the active agent to remain effective over the entire period of time of delivery to the patient through the drug delivery device. The presence of the graft moieties enhances the ability of the adhesive system to retain its structural integrity and adhesive character during the period of use of the drug delivery device. More specifically, the presence of a graft macromeric moiety containing hydrophilic repeat units enhances the compatibility of any drug flux enhancer with the graft copolymer.

The pharmacologically active agent to be administered by use of the transdermal drug delivery means is employed in a conventional manner. Suitable active agents include those that are compatible with the administration system of the present invention and exhibit the expected benefit upon percutaneous administration. Such active agents include, without limitation, antibiotics, antipyretics, analgesics, anti-inflammatory drugs, antihistaminics, psychotropic drugs, coronary vasodilators, antiarrhythmics, antihypertensives, chemotherapeutic drugs, anticancer agents, antiemetics, vitamins, antispasmodics, antitussives, antifungal drugs, steroids, etc. Exemplary of the most commonly transdermally-administered active agents are clonidine, estrodiol, nicotine, nitroglycerine and scopolamine, each commercially available in transdermal devices. See U.S. Patent No. 5,372,819, herein incorporated by reference, for a more detailed discussion of suitable percutaneous administered active agents.

In a preferred embodiment, estrogen and progestin may be administered by means of the present invention. The estrogen component may be either a synthetic or natural estrogen. Exemplary estrogen compounds include ethinyl estradiol, 17B estradiol, mestranol, estradiol valerate, 11-nitrato estradiol, 7-alpha-methyl-11-nitrato-estradiol, piperazine estrone sulfate, quinestranol and pharmaceutically acceptable derivatives thereof. Exemplary progestin components include progesterone, 17-hydroxyprogesterone, dihydroprogesterone, medroxyprogesterone acetate, norethindrone, norethindrone acetate, norethynodrel, ethynodiol diacetate, norgestrel, levo-norgestrel, gestodene, delta-15-levonorgestrel, norgestimate, 17-deacetyl norgestimate, nomegestrol, nesterone, desogestrel, and 3-keto-deogestrel.

The use of a graft copolymer as a transdermal adhesive matrix is taught by U.S. Patent No. 4,482,534. However, this patent is directed to a nitroglycerin adhesive preparation. The adhesive preparation disclosed in this patent may comprise a graft vinylpyrrolidone copolymer, either crosslinked or non-crosslinked. PCT publication WO 96/08229 also discloses a transdermal adhesive matrix comprised of a graft copolymer which may be used in association with estradiol or progestin. However, the disclosed adhesive does not achieve the balance of properties achieved by the present invention.

The adhesive may be used with particular advantage in association with a percutaneous penetration enhancer in a transdermal drug delivery device. Percutaneous penetration

enhancers have the ability to increase permeability of skin to transdermally-administered pharmacologically active agents. Such enhancers are well-known in the art, and are discussed at length in U.S. Patent Nos. 5,059,426 and 5,175,052, each herein incorporated by reference. By way of brief summary, such enhancers include but are not limited to surfactants (anionic, nonionic, cationic, zwitterionic), lipophilic solvents (terpenes, lactams), hydrophilic solvents (polyols, fatty acid esters, alcohols, sulfoxides), etc. Preferably, such enhancers are selected from the group consisting of sorbitols, ethoxylated alkyl phenols, glycerol, propylene glycol, polyethylene glycols, fatty acid esters, alcohols, and amines, and may be either water-soluble or non-water soluble (i.e. oily).

It has been found that the pressure sensitive adhesive of the present invention can be used with advantage upon admixture of percutaneous penetration enhancers with the base polymer to form a drug flux enhancer-tolerant pressure sensitive adhesive composition. That is, both oily or water-soluble percutaneous penetration enhancers can be admixed with the base polymer to maximize the ability of an incorporated pharmacologically active agent to be absorbed into the skin without adversely affecting the adhesive properties of the adhesive. Advantageously, it has been found that the percutaneous penetration enhancer can be used in amounts up to about 40 percent by weight, based on the weight of the composition, without adversely affecting the physical integrity of the adhesive or its adhesive properties. Such advantages can be attained

irrespective of whether the percutaneous penetration enhancer is either oil or water-soluble which result is not well-attained by conventional adhesives. Preferably, the enhancer
5 will be employed in an amount within the range of from 5 to 30 percent by weight, based on the weight of the composition.

The adhesive of the present invention may be used with advantage in a variety of conventional
10 transdermal drug delivery devices. Such devices may take many forms. Generally, such devices comprise a backing material and an adhesive layer on at least a portion of the backing material. A release liner covers the adhesive layer until use
15 at which time the liner is removed and the adhesive layer placed on the skin. The backing material is impermeable to the pharmacologically active agent. The pharmacologically active agent may be contained in either a liquid reservoir
20 within the backing layer, within a matrix layer on said backing layer disposed between the adhesive layer and the backing layer, or within a layer of the drug flux enhancer-adhesive composition of the present invention. The manner of formulation of
25 such various transdermal drug delivery systems is within the ability of one skilled in the art.

The pharmacologically active agent, in homogenous admixture with the pressure sensitive graft copolymer, is present in an amount effective
30 to provide the desired dosage to the patient. Generally, the active agent will be present in an amount within the range of from 0.5 to 30 percent by weight, based on the total weight of the composition. One skilled in the art can
35 readily determine the amount of pharmacologically

active agent to employ in association with the graft copolymer to achieve the desired degree of administration.

The adhesive of the present invention may also be used in association with a variety of body members (e.g., tapes, patches, strips, labels, etc.) to provide an adhesive assembly. For example, the body member may be in the form of a backing material coated on at least one side thereof with the adhesive to provide an adhesive-backed sheet film or tape. Exemplary backing materials used in the production of such a product include but are not limited to flexible and inflexible backing materials conventionally employed in the area of pressure sensitive adhesives, such as creped paper, kraft paper, fabrics (knits, non-wovens, wovens), foil and synthetic polymer films such as polyethylene, polypropylene, polyvinyl chloride, poly(ethylene terephthalate) and cellulose acetate, as well as glass, ceramics, metallized polymer films and other compatible sheet or tape materials.

The body member (e.g., in sheet form) may be coated in any conventional manner with the adhesive composition of the present invention, such as by roll coating, spray coating, extrusion coating, co-extrusion coating, hot melt coating by use of conventional coating devices. When appropriate, the adhesive of the present invention may be applied as a solution to at least one surface of the body member and the solvent subsequently removed to leave a tacky adhesive residue on the body member. The adhesive may be applied to the body member either in the form of a continuous layer or in discontinuous form.

In order to demonstrate the advantageous properties of the adhesive compositions of the present invention, various polymeric adhesive compositions were prepared having the compositions described in the following Examples.

EXAMPLE 1

A reaction mixture was prepared and 0.11 wt. % BPO was used as the catalyst. 30% of the mixture was charged to a 1-liter reaction vessel. Under a nitrogen atmosphere, the batch was heated to 72°C over 15 minutes. After the initial 15 minutes, the remaining 70% of monomer/solvent mixture was added over 4 hours, maintaining a batch temperature of 71.5-74°C. Upon completion of the addition, the reactants were polymerized for 1 additional hour to produce a tackifier-free pressure sensitive adhesive. The reactor feed mix consisted of the following components:

<u>Monomers</u>	<u>Amount</u>
(grams)	
Polystyrene methacrylate (macromer)	21.00
Ethoxylated nonyl-phenol acrylate (macromer)	25.84
Isooctyl acrylate (A monomer)	56.52
Hydroxy ethyl acrylate (B monomer)	64.60
Isobornyl acrylate (A monomer)	25.84
Lauryl acrylate (A monomer)	96.90
Stearyl acrylate (A monomer)	32.30
<u>Solvents</u>	<u>Amount</u>
(grams)	
Ethyl acetate	474.30
Toluene	52.70

EXAMPLE 2

The procedure of Example 1 was repeated using the following reactor feed components to produce a tackifier-free pressure sensitive adhesive with the exception that the reactants were added over 3.5 hours with a subsequent 1.5 hour reaction time:

	<u>Monomers</u>	<u>Amount</u> (grams)
10	Polystyrene methacrylate (macromer)	23.20
	Ethoxylated nonyl-phenol acrylate (macromer)	83.90
	Hydroxyl ethyl acrylate (B monomer)	71.40
	Lauryl acrylate (A monomer)	133.88
15	Stearyl acrylate (A monomer)	44.62
	<u>Solvents</u>	<u>Amount</u> (grams)
	Ethyl acetate	330.31
	Toluene	147.90
20	Isopropyl alcohol	14.79

EXAMPLE 3

The procedure of Example 1 was repeated using the following reactor feed components to produce a tackifier-free pressure sensitive adhesive with the exception that the reactants were added over 3.5 hours with a subsequent 1.5 hour reaction time:

	<u>Monomers</u>	<u>Amount</u> (grams)
30	Polystyrene methacrylate (macromer)	23.21
	Ethoxylated nonyl-phenol acrylate (macromer)	71.40

22

Hydroxyl ethyl acrylate (B monomer)	85.68
Lauryl acrylate (A monomer)	107.09
Stearyl acrylate (A monomer)	33.92
Isobornyl acrylate (A monomer)	35.70

5	<u>Solvents</u>	<u>Amount</u> (grams)
	Ethyl acetate	330.31
	Toluene	147.90
	Isopropyl alcohol	14.79

10

EXAMPLE 4

The procedure of Example 1 was repeated using the following reactor feed components to produce a tackifier-free pressure sensitive adhesive, with the exception that the reactants were added over 3.5 hours with a subsequent 1.5 hour reaction time:

15

	<u>Monomers</u>	<u>Amount</u> (grams)
	Tridecyl acrylate (A monomer)	178.50
20	Ethoxylated nonyl-phenol acrylate (macromer)	76.76
	Hydroxyl ethyl acrylate (B monomer)	71.40
	Polystyrene methacrylate (macromer)	30.34
	<u>Solvents</u>	<u>Amount</u> (grams)
25	Ethyl acetate	330.31
	Isopropyl alcohol	14.79
	Toluene	147.90

EXAMPLE 5

The procedure of Example 1 was repeated using the following reactor feed components to produce a tackifier-free pressure sensitive adhesive, with the exception that the reactants were added over 3 hours with a subsequent 1 hour reaction time:

<u>Monomers</u>		<u>Amount</u>
		(grams)
10	Isooctyl acrylate (A monomer)	144.00
	Ethoxylated nonyl-phenol acrylate (D macromer)	144.00
	Beta-carboxyethyl acrylate (D macromer) (n = 4-6)	16.20
	Beta-carboxyethyl acrylate (B monomer) (n = 2-3)	37.80
15	Polystyrene methacrylate (C macromer)	18.00
<u>Solvents</u>		<u>Amount</u>
		(grams)
20	Ethyl acetate	352.00
	Isopropyl alcohol	22.00
	Toluene	66.00

EXAMPLE 6

The procedure of Example 5 was repeated with the exception that the following components were added to the completed polymer product of Example 5 to yield a crosslinked adhesive:

- Foral 105 rosin tackifier (50% solution)
- Citroflex B-6 citric acid ester plasticizer (20% solution)
- Xama-7 aziridine crosslinker* (0.75%)

EXAMPLE 7

The procedure of Example 3 was repeated using the following reaction feed components to produce a tackifier-free pressure sensitive adhesive:

5	<u>Monomers</u>	<u>Amount</u>
		(grams)
	Isooctyl acrylate (A monomer)	72.00
	Tridecyl acrylate (A monomer)	72.00
	Ethoxylated nonyl-phenol acrylate	144.00
10	(D macromer)	
	Beta-carboxyethyl acrylate	16.20
	(D macromer) (n = 4-6)	
	Beta-carboxyethyl acrylate	37.80
	(B monomer) (n = 2-3)	
15	Polystyrene methacrylate	18.00
	(C macromer)	
	<u>Solvents</u>	<u>Amount</u>
		(grams)
	Ethyl acetate	352.00
20	Isopropyl alcohol	22.00
	Toluene	66.00

WHAT IS CLAIMED IS:

1. A normally tacky graft copolymer pressure sensitive adhesive comprised of a backbone polymer having a polymeric moiety grafted thereto, comprising the reaction product of:
- (1) at least one A monomer consisting of a monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol, said alcohol having from 1 to 30 carbon atoms, wherein at least about 30 percent by weight of said A monomer consists of a monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol having at least 12 carbon atoms, and said at least one A monomer exhibiting an average number of carbon atoms in the alcohol portion of the total acrylic or methacrylic acid esters of at least 10,
 - (2) at least one optional B monomer,
 - (3) an optional polymeric graft moiety C having a T_g greater than 20°C, and
 - (4) a graft macromer D containing repeat hydrophilic units.

2. A pressure sensitive adhesive drug delivery composition for use in the transdermal administration of a pharmacologically active agent comprised of a homogeneous admixture of a hydrophilic macromer reinforced copolymer and a pharmacologically active agent, said copolymer comprising the reaction product of:

- (1) at least one A monomer consisting of a monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol, said alcohol having from 1 to 30 carbon atoms, wherein at least about 30 percent by weight of said A monomer consists of a

monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol having at least 12 carbon atoms, and said at least one A monomer exhibiting an average number of carbon atoms in the alcohol
5 portion of the total acrylic or methacrylic acid esters of at least 10,

(2) optionally at least one B monomer,

(3) optionally a polymeric graft moiety C having a T_g greater than 20°C, and

10 (4) a graft macromer D containing hydrophilic repeat units.

3. A transdermal delivery system for administering a pharmacologically active agent comprising a flexible backing material impermeable
15 to said active agent and a pressure sensitive adhesive layer on at least a portion of said backing layer in homogeneous admixture with said active agent, said pressure sensitive adhesive comprising a graft macromer reinforced copolymer
20 formed by the reaction of:

(1) at least one A monomer consisting of a monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol, said alcohol having from 1 to 30 carbon atoms, wherein at least about 30
25 percent by weight of said A monomer consists of a monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol having at least 12 carbon atoms, and said at least one A monomer exhibiting an average number of carbon atoms in the alcohol
30 portion of the total acrylic or methacrylic acid esters of at least 10,

(2) optionally at least one B monomer,

(3) optionally a polymeric graft moiety C having a T_g greater than 20°C, and

(4) a graft macromer D containing hydrophilic repeat units.

4. The product of any one of claims 1-3 wherein said graft moiety C is a polymerized
5 monoalkenyl-substituted aromatic hydrocarbon.

5. The product of claim 4 wherein said polymerized monoalkenyl-substituted aromatic hydrocarbon comprises polystyrene.

6. The product of any one of claims 1-3
10 wherein said at least one A monomer comprises an ester of acrylic or methacrylic acid with a non-tertiary alcohol selected from the group consisting of 1-butanol, 1-pentanol, 2-pentanol, 3-pentanol, 2-methyl-1-butanol, 1-methyl-1-
15 pentanol, 2-methyl-1-pentanol, 3-methyl-1-pentanol, 2-ethyl-1-butanol, 3,5,5-trimethyl-1-hexanol, 3-heptanol, 2-octanol, 1-decanol, and 1-dodecanol.

7. The product of any one of claims 1-3
20 wherein the A monomer is present in the copolymer in an amount within the range of from about 20 to 80 percent by weight.

8. The product of any one of claims 1-3 wherein the B monomer is present in the copolymer
25 in an amount within the range of from about 3 to 30 percent by weight.

9. The product of any one of claims 1-3 wherein the D macromer is present in the copolymer

in an amount within the range of from about 5 to 60 percent by weight.

10. The product of any one of claims 1-3 wherein said B monomer is selected from the group consisting of hydroxy(C₁₋₅)alkyl acrylates, hydroxy(C₁₋₅)alkyl methacrylates, dihydroxy(C₁₋₅)alkyl acrylates, dihydroxy(C₁₋₅)alkyl methacrylates and mixtures thereof.


11. The product of any one of claims 1-3 wherein said B monomer is selected from the group consisting of acrylamide, methacrylamide, N-methylacrylamide, N-ethylacrylamide, N-methylolacrylamide, N-hydroxyethylacrylamide, diacetone acrylamide, N,N-dimethylacrylamide, N,N-diethylacrylamide, N-ethyl-N-aminoethyl acrylamide, N-ethyl-N-hydroxyethylacrylamide, N,N-dimethylolacrylamide, N,N-dihydroxyethylacrylamide and mixtures thereof.

12. The product of any one of claims 1-3 wherein said macromer D is defined by the formula $X-(Y)_p-Z-R$, wherein X is a moiety copolymerizable with monomers A and B or capable of attachment to copolymerized monomers A and B, Y is a divalent linking group, Z is a homo- or copolymeric moiety containing hydrophilic repeat units, R is a terminal group, and p is 0 or 1.

13. The product of claim 12 wherein Z is selected from the group consisting of a polyalkylene oxide radical, a polyethyloxazoline radical, a polyacrylic acid radical, a polyvinyl alcohol radical, a polyvinylpyrrolidone radical,


a polyvinylcaprolactam radical and a polymethylvinyl ether radical.

14. The product of any one of claims 1-3 wherein said macromer D is defined by the formula:



wherein X is a moiety copolymerizable with monomers A and B or capable of attachment to copolymerized monomers A and B, Y is a divalent linking group, R is a terminal group, m is an integer of from 2 to 6, n is an integer of from 5 to 300, and p is 0 or 1.

15. The product of claim 14 wherein said macromer D is defined by the formula



wherein R_1 is hydrogen or C_{1-5} alkyl, R is a terminal group, and n is an integer from 5 to 30.

16. The product of any one of claims 1-3 wherein said A monomer comprises a monomeric acrylic or methacrylic acid ester of a non-tertiary alcohol which has from 12 to 18 carbon atoms.


17. The product of any one of claims 1-3 wherein said macromer D is selected from the group consisting of ethoxylated and propoxylated hydroxy (C_{1-5} alkyl) (meth)acrylate, poly(2-ethyl-2-oxazoline), polyacrylic acid, polyvinyl alcohol, polyvinyl pyrrolidone, polyvinyl caprolactam and polymethylvinyl ether mono(meth)acrylate.

18. The product of any one of claims 1-3 wherein said B monomer is an N-vinyl lactam monomer selected from the group consisting of N-vinyl-2-pyrrolidone, 5-methyl-N-vinyl-2-pyrrolidone, 5-ethyl-N-vinyl-2-pyrrolidone, 3,3-dimethyl-N-vinyl-2-pyrrolidone, 3-methyl-N-vinyl-2-pyrrolidone, 3-ethyl-N-vinyl-2-pyrrolidone, 4-methyl-N-vinyl-2-pyrrolidone, 4-ethyl-N-vinyl-2-pyrrolidone, N-vinyl-2-valerolactam, N-vinyl-2-caprolactam, and mixtures thereof.

19. The product of any one of claims 1-3 wherein said copolymer comprises the reaction product of at least one A monomer, at least one N-vinyl lactam B monomer, at least one polymeric graft moiety C and a graft macromer D.


20. The product of any one of claims 2-3 wherein said pharmacologically active agent is selected from the group consisting of estrogen, progestin and mixtures thereof.

21. The product of any one of claims 1-3 wherein said macromer D is defined by the formula:



wherein X is a moiety copolymerizable with monomers A and B or capable of attachment to copolymerized monomers A and B, Y is a divalent linking group, R is a terminal group, m is an integer of from 2 to 6, n is an integer of up to 300, and p is 0 or 1.

22. The product of claim 21 wherein said macromer D is defined by the formula:



wherein R_1 is hydrogen or C_{1-5} alkyl, m is 2 or 3,
 n is 4 to 30, and R is H, OH, C_{1-5} alkyl or nonyl-
 5 phenol.

23. The product of claim 21 wherein R is OH,
 C_{1-5} alkyl, or nonyl-phenol.

24. The product of claim 21 wherein n is an
 integer of from 4 to 30.

INTERNATIONAL SEARCH REPORT

Int. Application No
PCT/US 98/02696

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F290/04 C08L51/00 C09J151/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F A61K C08L C09J A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 732 100 A (ADHESIVES RES INC) 18 September 1996	1-9, 11-17
Y	* see page 3, line 20-21 ; page 3, line 52 - page 4, line 16 ; page 4, line 30 -page 5, line 42 * see page 3, line 8-51	10, 18-24
X	EP 0 554 106 A (ADHESIVES RES INC) 4 August 1993 * page 3, line 53 - 55 ; page 3, line 24 - page 5, line 35 * see page 16, line 28 - page 17, line 6	1-9, 11-17
X	US 4 554 324 A (HUSMAN JAMES R ET AL) 19 November 1985 * claims 1-8 ; column 4, line 6-8 * see column 4, line 60 - column 6, line 54	1, 6-9, 11-13, 16
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

14 July 1998

Date of mailing of the international search report

20/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hammond, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/02696

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 242 951 A (AKEMI HITOSHI ET AL) 7 September 1993 cited in the application see column 3, line 30-66; claims 1-11	18-20
Y	EP 0 728 780 A (ROEHM GMBH) 28 August 1996 * see page 2, line 33 - page 3, line 32 * see page 2, line 57	21-24
Y	WO 95 14746 A (ADHESIVES RES INC ;ZAJACZKOWSKI MICHAEL J (US)) 1 June 1995 see page 26, line 26-29	10

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. l. Application No

PCT/US 98/02696

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0732100 A	18-09-1996	US 5573778 A	12-11-1996
		AU 4808596 A	26-09-1996
		CA 2171911 A	18-09-1996
		JP 8319464 A	03-12-1996
EP 0554106 A	04-08-1993	US 5352516 A	04-10-1994
		AT 136576 T	15-04-1996
		CA 2088457 A	01-08-1993
		DE 69302107 D	15-05-1996
		DE 69302107 T	29-08-1996
US 4554324 A	19-11-1985	US 5057366 A	15-10-1991
		AU 559174 B	26-02-1987
		AU 1916183 A	22-03-1984
		BR 8305024 A	08-05-1984
		CA 1241479 A	30-08-1988
		EP 0104046 A	28-03-1984
		JP 1976563 C	17-10-1995
		JP 5032438 B	17-05-1993
		JP 59075975 A	28-04-1984
US 5242951 A	07-09-1993	AT 124872 T	15-07-1995
		CA 2033113 A,C	29-06-1991
		DE 69020875 D	17-08-1995
		DE 69020875 T	14-12-1995
		DK 435200 T	20-11-1995
		EP 0435200 A	03-07-1991
		ES 2075129 T	01-10-1995
		GR 3017650 T	31-01-1996
		CA 2033109 A	29-06-1991
		DE 69010317 D	04-08-1994
		DE 69010317 T	20-10-1994
		DE 69026361 D	09-05-1996
		DE 69026361 T	14-08-1996
		EP 0435199 A	03-07-1991
		EP 0436203 A	10-07-1991
		ES 2055291 T	16-08-1994
		JP 2700835 B	21-01-1998
		JP 3220120 A	27-09-1991
		JP 3220121 A	27-09-1991

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/02696

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5242951 A		JP 3223212 A	02-10-1991
		US 5204109 A	20-04-1993
		US 5298258 A	29-03-1994
EP 0728780 A	28-08-1996	DE 19506399 A	29-08-1996
		JP 8245731 A	24-09-1996
WO 9514746 A	01-06-1995	US 5395907 A	07-03-1995
		AU 1330895 A	13-06-1995
		CA 2154483 A	01-06-1995
		EP 0681601 A	15-11-1995
		US 5508367 A	16-04-1996
		US 5565268 A	15-10-1996
		US 5726250 A	10-03-1998
		US 5731387 A	24-03-1998

THIS PAGE BLANK (USPTO)